

BENCHMADE[®] TABLE OF STEELS

STEEL	CARBON	CHROMIUM	COBALT	NITROGEN	MANGANESE	MOLYBDENUM	NICKEL	PHOSPHOROUS	SILICON	SULPH	TUNGSTEN	VANADIUM	HRC
154CM	1.05	14.00	-	-	0.50	4.00	-	-	0.30	-	-	-	58-61
S30V	1.45	14.00	-	-	0.50	2.00	-	-	0.50	-	-	4.00	58-60
X15 T.N	0.40	16.00	-	-	-	2.00	-	< 0.02	-	< 0.005	-	0.35	58-60
M2	0.85	4.15	-	0.30	0.30	5.00	0.30	-	0.30	-	5.50-6.75	1.95	58-60
D2	1.50	12.00	-	0.30	0.60	1.00	0.30	-	0.60	-	-	1.00	60-62
M390	1.90	20.00	-	-	.30	1.00	-	-	.60	-	.60	4.00	60-62
N680	0.54	17.30	-	-	.40	1.10	-	-	.45	-	-	.10	58-60
N690	1.07	17.00	1.50	-	0.40	1.10	-	-	0.40	-	-	0.10	58-60
440C	1.00	17.00	-	-	1.00	0.75	-	0.04	1.00	0.03	-	-	58-60
8CR14MOV	0.75	14.50	-	-	1.00	0.20	-	0.03	1.00	0.03	-	0.20	57-58
AUS-8	0.75	14.00	-	0.49	0.50	0.10	0.49	0.04	1.00	0.03	-	0.20	58-59
1095	1.00	-	-	-	0.40	-	-	0.04	-	0.05	-	-	57-60
9CR13COMOV	0.85	13.50	1.00	-	1.00	0.20	-	-	-	-	-	0.20	58-60
CPM-M4	1.42	4.0	-	-	-	5.25	-	-	-	-	5.5	4.0	62-64

{If your browser resizes images, click image to resize to original.}